



## M- REJUN POOL

### **FLEXIBLE MORTAR FOR BRICK JOINT SEALING, HIGH ADHESION, SUITABLE FOR PERMANENT IMMERSION (JOINT 2 TO 20 mm)**

M-REJUN POOL is a product formulated with cement, pure silica, and special aggregates that give it properties for crack repair and sealing of brick joints, as well as for sealing and waterproofing grout in mosaic or ceramic tiles in permanent contact with water, architectural stone, and joints in various types of construction units.

#### **APPLICATIONS**

Grouting all types of ceramic tiles in vertical and horizontal surfaces.  
Restoration of deteriorated joints in brickwork.  
Sealing and waterproofing mosaic or ceramic joints in permanent contact with water.  
Sealing between different types of construction units.

#### **ADVANTAGES**

Compensated shrinkage and good adhesion to the substrate.  
High durability without requiring maintenance.  
Excellent structural strength.  
Waterproofs the treated joint against rainwater.  
Can be manufactured in a special color to match the construction unit's needs.  
High color stability.  
Contains no metallic elements.

#### **METHOD OF USE**

##### **Surface Preparation**

Do not apply M-REJUN POOL until at least 24-48 hours have passed since the installation of ceramic tiles with cement-based adhesives.

The surfaces of the joints and the edges of the tiles must be clean, free of dust, grease, and residue from mortar or adhesive used during tile installation, or any other substance that could affect the product's adhesion. Before applying the mortar, saturate the edges of the joint without leaving standing water.

##### **Mix Preparation**

Mix manually or with an electric mixer 1.45 liters of clean water for every 5 kg of M-REJUN POOL (or proportionally if using more or less mortar) until a homogeneous, creamy mixture without lumps is achieved. The amount of water in the mix can be adjusted to facilitate application; however, excessive mixing water may cause visible shrinkage of the joint.

Let the mixture rest for 5 minutes before application.

The joints will be filled by pressing the paste with a spatula or rubber trowel, spreading the product diagonally, or with a refillable caulking gun.

Wait until the paste is no longer plastic (the paste becomes opaque, it is no longer shiny), then clean with a damp sponge or remove excess paste dry with a spatula. Do not start too early, as this could partially empty the joint, and do not let it dry completely, as this could damage the surface of the tiles. The time until the paste becomes opaque ranges from 10 minutes to several hours depending on the joint size and environmental conditions.

#### **SAFETY AND HYGIENE**

M-REJUN POOL is not a toxic product but is abrasive in its composition. Avoid contact with skin and eyes, as well as inhalation of dust.

Use gloves and safety glasses when handling, mixing, and applying the product.

In case of skin contact, wash the affected area with water and soap. In case of splashes or eye contact, rinse thoroughly with clean water without rubbing. If irritation persists, consult a doctor



**Tecno Prodíst®**

Chemical solutions for construction and maintenance

[www.tecnoprodíst.com](http://www.tecnoprodíst.com)