



## **RENOVATEC CORONA APPLICATION EXECUTION PROCESS**

### **CLEANING THE STONE (VERY IMPORTANT FOR A GOOD GRIP OF THE PRODUCT)**

1 - Wet the stone, mix TECNOCLEAN PISCINAS and water in a 1 x 4 water sprayer, spray the entire stone and let it sit for 15 minutes, then rinse with a pressure washer or if not available, with a hose and pressurized water

#### **TECNOCLEAN PISCINAS:**

<https://www.tecnoprodista.eu/en/swimming-pools/167-tecnoclean-pools.html>

2 - LET IT DRY AFTER CLEANING FOR A MINIMUM OF 3 DAYS, 4 days is even better, so that all the moisture from the cleaning we have done is removed.

3- In a separate bucket, dilute our RENOVATEC CORONA paint with 20% water and apply the first coat

#### **RENOVATEC CORONA:**

<https://www.tecnoprodista.eu/en/swimming-pools/109-renovatec-corona.html>

4 – After a minimum of 6 hours of drying of the first coat, apply the second coat pure or with a maximum of 5% water, do not wet the surface after applying the product in 48 h – 72 h

#### **CONSUMPTION:**

On a porous stone that has not been painted previously, the approximate yield of the two coats is 2 – 3 m<sup>2</sup> for the two coats per kg of product

Please follow the application instructions to achieve optimal results and product durability

Information provided by: TECNO PRODISTA TECHNICAL DEPARTMENT